



QUALITEK®

Paste Flux PF200, PF400, PF600, PF700

DESCRIPTION

PF200, PF400, PF600 are mixtures of high grade synthetic resin, rosins and thixotropic thickeners. Residues after soldering are non-corrosive, non-conductive and highly insulated. PF700 is a mixture of organic acid, thixotropic thickeners and surfactants, which aid in water removal of post soldering residues.

BENEFITS

- Rapid wetting on virtually all types of substrates
- High tack force
- Long tack time

APPLICATION METHODS

Paste Fluxes are recommended for touch up and repair of surface mount assemblies. Paste Fluxes may be brushed or dispensed on the appropriate areas, then heated using conventional methods.

RESIDUE REMOVAL

PF200, PF600 are non-corrosive, non-conductive and highly insulated therefore residue removal is not required. Post soldering residues from PF200, PF400, and PF600 may be removed with CFC substitutes or Qualitek #1005 buffered saponifier). PF700 requires only hot DI water (120°F) for residue removal.

Qualitek® is a trademark of Qualitek International, Inc.

PHYSICAL & CHEMICAL CHARACTERISTICS

	PF200	PF400	PF600	PF700
Color & Appearance	Amber Paste	Amber Paste	Amber Paste	Amber Paste
W.E.R.	>100,000 ohms	>100,000 ohms	>100,000 ohms	N / A
pH	5.0 – 5.7	4.0 – 4.6	5.1 – 5.7	2.6 – 2.8
Copper Mirror Test	Pass	Pass	Pass	Pass
Silver Chromate Test	Pass	Pass	Pass	Pass
Surface Insulation Resistance (ohms)	>1.0x10 ⁹	>1.0x10 ⁹	>1.0x10 ⁹	>1.0x10 ⁹
Storage Temperature	72 - 80°F	72 - 80°F	72 - 80°F	35 - 65°F
Shelf Life	1 Year	1 Year	1 Year	6 Months

TEL: (630) 628-8083 FAX: (630) 628-6543 E-MAIL: solder@qualitek.com HOME PAGE: <http://www.qualitek.com>

HEADQUARTERS: 315 Fairbank St., Addison, IL 60101 U.S.A.

WORLDWIDE BRANCHES: UNITED KINGDOM – MEXICO – CHINA – PHILLIPINES - SINGAPORE

QUALITEK INTERNATIONAL, INC. AN ISO 9002 CERTIFIED COMPANY

This data is based on information that the manufacturer believed to be reliable and offered in good faith. Qualitek International, Inc. makes no warranties expressed or implied as to its accuracy and assumes no responsibilities and liabilities arising out of its use by others as conditions and methods of use of the products is beyond the control of Qualitek International, Inc. The user must determine the suitability of the product before using it on a commercial basis. The warranties extend only to the conformity of the product to the physical descriptions. In no event will Qualitek International, Inc. be responsible for special, incidental and consequential damages whether the claim is in contract, negligence or otherwise.

Rev: 080499-Pasteflux

Consult MSDS for health and safety information